## SPECIFICATION DATA SHEET

# MCC-A

#### **EnCore® Combined Materials/Mechanically Clad Composite**

**Description**MCC-A is a high performance gasket material combining an inorganic fiber-based core with 0.2mm (0.008") perforated tin-plated steel facings on one or both sides. It is ideally suited for high temperature applications including exhaust manifold and header gaskets, engine heat shields, furnace and HVAC shielding, and small engine head and muffler gaskets. MCC-A is thermally stable and can be used to seal hot gases up to 760°C (1400°F) when properly clamped between flanges. The typical values below were established using only the fiber core without cladding, with a thickness of 1.0mm (0.039"). Double-clad material is available in 1.2mm (0.047") and 1.6mm (0.062") thicknesses, and single clad material is available in 1.0mm (0.039") and 1.2mm (0.047") thicknesses.

### Specification Properties

Property	<u>Value</u>	<u>Method</u>
Density, g/cc(lb/cu.ft)	0.897 - 1.026 (56 - 64)	ASTM F 1315
Compressibility, % (at 6.9MPa)	21 - 39	ASTM F 36
Recovery, %	35 (min.)	ASTM F 36
Tensile Strength, AMD, MPa(psi)	4.83 (700) (min.)	ASTM F 152
Weight Loss on Ignition, % (at 815°C)	32 (max.)	ASTM F 495
Fluid Resistance, IRM903 Oil		ASTM F 146
Change in Weight, %	70 (max.)	
Fluid Resistance, Fuel B		ASTM F 146
Change in Weight, %	65 (max.)	
Fluid Resistance, Distilled Water		ASTM F 146
Change in Weight, %	70 (max.)	

#### Remarks and Related Documents

Specification values determined by the test methods required for ASTM F-104, Type 3 materials.

FnCore®, Hydro-Fused®, MicroPore®, Pro-Formance®, Select-a-Shield®, Syntheseal®, Thermo-Tork®, and Voltoid® are registered trademarks of Interface Performance Materials, Inc. PureGuard™ is a trademark of Interface Performance Materials.

WARNING: The description and performance data provided herein constitute a material specification for quality control purposes, but do not imply suitability for use in a specific application. Your specific application should not be undertaken without independent study and evaluation for suitability. Failure to select proper sealing products may result in either property damage or personal injury. For specific application recommendations, contact Interface Performance Materials. INTERFACE PERFORMANCE MATERIALS EXPRESSLY DISCLAIMS ALL WARRANTIES EITHER EXPRESS OR IMPLIED, INCLUDING ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO EVENT WILL INTERFACE BE LIABLE FOR ANY INDIRECT, SPECIAL, INCIDENTAL, CONSEQUENTIAL OR PUNITIVE DAMAGES, HOWEVER CAUSED AND ON ANY THEORY OF LIABILITY, WHETHER IN CONTRACT, STRICT LIABILITY, OR TORT (INCLUDING NEGLIGENCE OR OTHERWISE) ARISING IN ANY WAY OUT OF THE USE OF THE INFORMATION CONTAINED IN ITS SPECIFICATION DATA SHEETS, ITS PRODUCTS OR THEIR FUTURE USE BY YOU OR ANY THIRD PARTIES, EVEN IF ADVISED OF THE POSSIBILITY OF SUCH DAMAGE.

Revised 06/20/17 Form SPDS-01 6/13/17 ©2017 Interface Performance Materials, Inc. For more information, please visit www.InterfaceMaterials.com or contact

WORLD HEADQUARTERS Interface Performance Materials, Inc. 216 Wohlsen Way Lancaster, PA 17603 +1.717.207.6000

**TECHNICAL CENTER** Interface Performance Materials, Inc. 215 Wohlsen Way Lancaster, PA 17603 USA AE@InterfaceMaterials.com +1.717.207.6000

NORTH AMERICA Interface Performance Materials, Inc. 22260 Haggerty Road, Suite 200 Northville, MI 48167 +1.248.596.2800

ASIA PACIFIC Interface Sealing Solutions Shanghai Co., LTD Unit 14F, No. 728 Yan An Road West, Changning District Shanghai 200050 China +8621.5238.5650

# Interface Performance Materials India LLP Mandkola Road, Vill. Atta, Sohna,

Distt: Mewat, Nuh-122103 (Haryana) +91.0124.8930992166

**EUROPE & SOUTH AMERICA** Interface Sealing Solutions Europe Lili Pean, Le Bourg Bonloc 64240 France +33.5.5929.1220

**GERMANY** Interface Performance Materials Altenkirchen GmbH P.O. Box 12 63 Koblenzer Strasse Altenkirchen D-57610 Germany +49.2681.80020

