SPECIFICATION DATA SHEET

SAS-221

Select-a-Seal®/Rubber Edged Composite Gasket

Description

SAS-221 combines a low density fiber carrier with a styrene butadiene rubber sealing bead. It is used for sealing water and coolant mixtures in applications that require the carrier to conform to extreme irregularities such as plastic parts, as-cast aluminum, and thin metal stampings. It is intended for continuous service at temperatures up to 125°C (257°F).

Specification Properties

<u>Property</u> Carrier Material	<u>Value</u> SAS-2	Method
General Description of Carrier	Low density, nitrile butadiene bound material with reinforced cellulose fiber.	
Caliper, mm(inch)	1.0, 1.2 (0.039, 0.047)	ASTM F 104
Density, g/cc(lb/cu.ft)	0.87 (54) (min.)	ASTM F 1315
Compressibility, % (at 34.5MPa)	28 - 42	ASTM F 36
Recovery, %	20 (min.)	ASTM F 36
Tensile Strength, AMD, MPa(psi)	8.62 (1250) (min.)	ASTM F 152
Polymer Edge	SAS-21	
General Description of Polymer	Styrene Butadiene Rubber Blend, generally used for water and coolant applications.	
ASTM Classification	M1CA503	ASTM D 2000
Temperature Rating, °C(°F)	125 (257)	ASTM D 2000
Durometer Hardness, Type A	45 - 55	ASTM D 2240
Tensile Strength, Initial, MPa(psi)	3 (345) (min.)	ASTM D 412
Edge Height	Specified on part drawing.	ISI M10.4X102

Remarks and Related Documents

Carrier specification values determined by the test methods required for ASTM F-104, Type 7 materials. Carrier is available with release coating per ISI 123316. Carrier caliper and release coating, and polymer edge height are specified on part drawing.

EnCore®, Hydro-Fused®, MicroPore®, Pro-Formance®, Select-a-Seal®, Select-a-Shield®, Syntheseal®, Thermo-Tork®, and Voltoid® are registered trademarks of Interface Performance Materials, Inc. PureGuard™ is a trademark of Interface Performance Materials.

WARNING: The description and performance data provided herein constitute a material specification for quality control purposes, but do not imply suitability for use in a specific application. Your specific application should not be undertaken without independent study and evaluation for suitability. Failure to select proper sealing products may result in either property damage or personal injury. For specific application recommendations, contact Interface Performance Materials. INTERFACE PERFORMANCE MATERIALS EXPRESSLY DISCLAIMS ALL WARRANTIES EITHER EXPRESS OR IMPLIED, INCLUDING ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO EVENT WILL INTERFACE BE LIABLE FOR ANY INDIRECT, SPECIAL, INCIDENTAL, CONSEQUENTIAL OR PUNITIVE DAMAGES, HOWEVER CAUSED AND ON ANY THEORY OF LIABILITY, WHETHER IN CONTRACT, STRICT LIABILITY, OR TORT (INCLUDING NEGLIGENCE OR OTHERWISE) ARISING IN ANY WAY OUT OF THE USE OF THE INFORMATION CONTAINED IN ITS SPECIFICATION DATA SHEETS, ITS PRODUCTS OR THEIR FUTURE USE BY YOU OR ANY THIRD PARTIES, EVEN IF ADVISED OF THE POSSIBILITY OF SUCH DAMAGE.

Revised 07/06/17 Form SPDS-01 6/13/17 ©2017 Interface Performance Materials, Inc. For more information, please visit www.InterfaceMaterials.com or contact

WORLD HEADQUARTERS Interface Performance Materials, Inc. 216 Wohlsen Way Lancaster, PA 17603 USA +1.717.207.6000

TECHNICAL CENTER
Interface Performance Materials, Inc.
215 Wohlsen Way
Lancaster, PA 17603
USA
AE@InterfaceMaterials.com
+1.717.207.6000

NORTH AMERICA Interface Performance Materials, Inc. 22260 Haggerty Road, Suite 200 Northville, MI 48167 USA +1.248.596.2800

ASIA PACIFIC
Interface Sealing Solutions Shanghai Co., LTD
Unit 14F, No. 728
Yan An Road West, Changning District
Shanghai 200050
China
+8621.5238.5650

INDIA

Interface Performance Materials India LLP Mandkola Road, Vill. Atta, Sohna, Distt: Mewat, Nuh-122103 (Haryana) +91.0124.8930992166

EUROPE & SOUTH AMERICA Interface Sealing Solutions Europe Lili Pean, Le Bourg Bonloc 64240 France +33.5.5929.1220

GERMANY Interface Performance Materials Altenkirchen GmbH P.O. Box 12 63 Koblenzer Strasse Altenkirchen D-57610 Germany +49.2681.80020

